


TECHNICAL INFORMATION

	IMPERIAL	METRIC
Max Production Width	118.11in	3000mm
Total Thickness	0.07in	1.8mm
Mass	0.43lb/ft ²	2.1kg/m ²
Tensile force at 1% elongation (static)	46lb/in Internal Method - ref. ISO 21181	8N/mm
Working Temp.	+14/+158F ^o	-10/+70C ^o
Flexion (A)	1.57in 40mm	
Counter Flexion (B)	1.57in 40mm	

COEFFICIENT OF FRICTION (bottom side) - **Steel** 0.24

BEST USED FOR

GENERAL CHARACTERISTICS

2 ply bare by bare PVC. Food approved

RECOMMENDED USES

Slider Bed | Flat Rollers | Slider Beds on Both Sides | Conveyor with Accumulation | Slide Bed with Pressure

SPECIAL CHARACTERISTICS

- ✓ **Food Approved, FDA compliance**
acc.to 21 CFR parts 170-19
- ✓ **Food Approved, EU compliance**
(EC) No. 1935/2004 & (EU) No. 10/2011

BELT CONSTRUCTION INFORMATION

TOP SIDE (Carrying)		TENSION MEMBER		BOTTOM SIDE (Pulley)	
Material	Fabric	Interply	PVC	Material	Fabric
Color	Fabric (FA)	Weft	Rigid (R)	Color	Fabric (FA)
Thickness	0in 0mm	Plies	2	Thickness	0in 0mm
Hardness ISO 868	-	Fabric	Light Rigid (LR)	Hardness ISO 868	-
Surface	Bare (00)			Surface	Bare (00)

*Because of continuous development above data is subjected to change without prior notice by Sampla. This data replaces that included in previous publications. Sampla excludes any liability for the incorrect use of the above stated information.